

Spezifikation / Specification

Schaum / Foam :	Cellpur R 5045																																																																						
Farbe / Colour :	türkis / turquoise																																																																						
Artikel Nr. / Article no. :	750304																																																																						
<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 50%;"></th> <th style="width: 10%;"></th> <th style="width: 10%;"></th> <th style="width: 10%;">Minimum</th> <th style="width: 10%;">Maximum</th> <th style="width: 10%;"></th> </tr> </thead> <tbody> <tr> <td>Materialdichte netto / Net Density</td> <td></td> <td>EN ISO 845</td> <td style="text-align: center;">45,0</td> <td style="text-align: center;">50,0</td> <td style="text-align: right;">[kg / m³]</td> </tr> <tr> <td>Stauchhärte / Compression Load Deflection (CLD)</td> <td style="text-align: center;">40% press</td> <td>EN ISO 3386-1</td> <td style="text-align: center;">4,0</td> <td style="text-align: center;">5,0</td> <td style="text-align: right;">[kPa]</td> </tr> <tr> <td>Elastizität / Elasticity</td> <td></td> <td>DIN 53 573</td> <td style="text-align: center;">60</td> <td style="text-align: center;">...</td> <td style="text-align: right;">[%]</td> </tr> <tr> <td>Zugfestigkeit / Tensile Strength</td> <td></td> <td>EN ISO 1798</td> <td style="text-align: center;">100</td> <td style="text-align: center;">...</td> <td style="text-align: right;">[kPa]</td> </tr> <tr> <td>Dehnung / Elongation At Break</td> <td></td> <td>EN ISO 1798</td> <td style="text-align: center;">100</td> <td style="text-align: center;">...</td> <td style="text-align: right;">[%]</td> </tr> <tr> <td>Luftdurchlässigkeit / Air Permeability</td> <td></td> <td>ASTM D 1564</td> <td style="text-align: center;">0</td> <td style="text-align: center;">...</td> <td style="text-align: right;">[L / min]</td> </tr> <tr> <td>Wet Compression Set</td> <td style="text-align: center;">(50 °C, 95 % rel, 70 % press, 22 h)</td> <td>Renault 1637</td> <td style="text-align: center;">...</td> <td style="text-align: center;">15</td> <td style="text-align: right;">[%]</td> </tr> <tr> <td>Compression Set</td> <td style="text-align: center;">(70 °C, 50 % rel, 50 % press, 22 h)</td> <td>EN ISO 1856-A</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> <td style="text-align: right;">[%]</td> </tr> <tr> <td>DVR / Compression Set B</td> <td style="text-align: center;">(23 °C, 50 % rel, 50 % press, 72 h)</td> <td>EN ISO 1856-B</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> <td style="text-align: right;">[%]</td> </tr> <tr> <td>Eindrückhärte / Indentation Load Deflection (ILD)</td> <td style="text-align: center;">40% press</td> <td>EN ISO 2439-C</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> <td style="text-align: right;">[N]</td> </tr> </tbody> </table>									Minimum	Maximum		Materialdichte netto / Net Density		EN ISO 845	45,0	50,0	[kg / m ³]	Stauchhärte / Compression Load Deflection (CLD)	40% press	EN ISO 3386-1	4,0	5,0	[kPa]	Elastizität / Elasticity		DIN 53 573	60	...	[%]	Zugfestigkeit / Tensile Strength		EN ISO 1798	100	...	[kPa]	Dehnung / Elongation At Break		EN ISO 1798	100	...	[%]	Luftdurchlässigkeit / Air Permeability		ASTM D 1564	0	...	[L / min]	Wet Compression Set	(50 °C, 95 % rel, 70 % press, 22 h)	Renault 1637	...	15	[%]	Compression Set	(70 °C, 50 % rel, 50 % press, 22 h)	EN ISO 1856-A	[%]	DVR / Compression Set B	(23 °C, 50 % rel, 50 % press, 72 h)	EN ISO 1856-B	[%]	Eindrückhärte / Indentation Load Deflection (ILD)	40% press	EN ISO 2439-C	[N]
			Minimum	Maximum																																																																			
Materialdichte netto / Net Density		EN ISO 845	45,0	50,0	[kg / m ³]																																																																		
Stauchhärte / Compression Load Deflection (CLD)	40% press	EN ISO 3386-1	4,0	5,0	[kPa]																																																																		
Elastizität / Elasticity		DIN 53 573	60	...	[%]																																																																		
Zugfestigkeit / Tensile Strength		EN ISO 1798	100	...	[kPa]																																																																		
Dehnung / Elongation At Break		EN ISO 1798	100	...	[%]																																																																		
Luftdurchlässigkeit / Air Permeability		ASTM D 1564	0	...	[L / min]																																																																		
Wet Compression Set	(50 °C, 95 % rel, 70 % press, 22 h)	Renault 1637	...	15	[%]																																																																		
Compression Set	(70 °C, 50 % rel, 50 % press, 22 h)	EN ISO 1856-A	[%]																																																																		
DVR / Compression Set B	(23 °C, 50 % rel, 50 % press, 72 h)	EN ISO 1856-B	[%]																																																																		
Eindrückhärte / Indentation Load Deflection (ILD)	40% press	EN ISO 2439-C	[N]																																																																		
Brandverhalten / Fire Resistance																																																																							
<table border="1" style="width: 100%; border-collapse: collapse;"> <tbody> <tr> <td rowspan="10" style="vertical-align: top;"> EUFAC Test (Cigarette) </td> <td></td> <td>EN 1021-1</td> <td style="text-align: center;">OK</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>EN 1021-2</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>UNI 9175</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>California 117 (2000)</td> <td style="text-align: center;">OK</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>MVSS 302</td> <td style="text-align: center;">OK</td> <td style="text-align: center;">SE / NBR</td> </tr> <tr> <td></td> <td>EN ISO 13501-1</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td rowspan="5" style="vertical-align: top;"> Vertical Test 12 sec. </td> <td style="text-align: center;">FAR 25.853 + smoke + toxicity</td> <td></td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>DIN 5510-2</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>DIN 4102-1</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>BS 5852 Crib 5</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>ÖNORM A 3800</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>ÖNORM S 1457</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> <tr> <td></td> <td>CH 5.2.</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> </tr> </tbody> </table>						EUFAC Test (Cigarette)		EN 1021-1	OK	...		EN 1021-2		UNI 9175		California 117 (2000)	OK	...		MVSS 302	OK	SE / NBR		EN ISO 13501-1	Vertical Test 12 sec.	FAR 25.853 + smoke + toxicity			DIN 5510-2		DIN 4102-1		BS 5852 Crib 5		ÖNORM A 3800		ÖNORM S 1457		CH 5.2.												
EUFAC Test (Cigarette)		EN 1021-1	OK	...																																																																			
		EN 1021-2																																																																			
		UNI 9175																																																																			
		California 117 (2000)	OK	...																																																																			
		MVSS 302	OK	SE / NBR																																																																			
		EN ISO 13501-1																																																																			
	Vertical Test 12 sec.	FAR 25.853 + smoke + toxicity																																																																			
			DIN 5510-2																																																																		
			DIN 4102-1																																																																		
			BS 5852 Crib 5																																																																		
		ÖNORM A 3800																																																																			
	ÖNORM S 1457																																																																				
	CH 5.2.																																																																				
sonstige / other																																																																							
<table border="1" style="width: 100%; border-collapse: collapse;"> <tbody> <tr> <td style="width: 50%;">ÖKO-TEX Standard 100</td> <td></td> <td></td> <td style="text-align: center;">OK</td> <td style="text-align: center;">product class 1</td> <td></td> </tr> <tr> <td>CertiPur Standard</td> <td></td> <td></td> <td style="text-align: center;">OK</td> <td style="text-align: center;">...</td> <td></td> </tr> <tr> <td>IKEA IOS-MAT-0010</td> <td></td> <td></td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> <td></td> </tr> <tr> <td>EN / IEC 61340-5-1</td> <td style="text-align: center;">electrostatic</td> <td style="text-align: center;">100 V , 20 sec</td> <td style="text-align: center;">...</td> <td style="text-align: center;">...</td> <td style="text-align: right;">Ohm [Ω]</td> </tr> </tbody> </table>						ÖKO-TEX Standard 100			OK	product class 1		CertiPur Standard			OK	...		IKEA IOS-MAT-0010				EN / IEC 61340-5-1	electrostatic	100 V , 20 sec	Ohm [Ω]																																										
ÖKO-TEX Standard 100			OK	product class 1																																																																			
CertiPur Standard			OK	...																																																																			
IKEA IOS-MAT-0010																																																																					
EN / IEC 61340-5-1	electrostatic	100 V , 20 sec	Ohm [Ω]																																																																		
erstellt / created	letzte Änderung / last change		Freigabe / free																																																																				
04.07.2012	23.04.2013		23.04.2013																																																																				
QM	QM		QM																																																																				